

TAVOLO

Finishing oil for wooden tables and countertops
High solids content

Tavolo is a finishing oil with a high solids content designed for wooden food surfaces such as tables, countertops and butcher blocks. Tavolo colours, seals, waterproofs and provides resistance to abrasion.



Number of Coats	2 coats
Drying Time	Between coats: 18 to 24 hours Handle with care: 24 to 48 hours Full cure: 7 days First cleaning: after 10 days
Available Colors	00 Colourless, 01 Cherry, 03 Medium Oak, 04 Charcoal, 06 Red Fox, 08 American Walnut, 11 Choco Wood, 13 Maple Brown, 15 Dark Oak, 17 Old Pine, 19 White, 20 Cappuccino, 21 Grey, 22 Natural, 23 Teak, 25 Burnt Wood, 26 Sand, 36 Smokey, 41 Ash Grey, 43 Driftwood, 44 Pale Walnut and 45 Pebble
Available Sizes	20 ml (Sample), 500 ml
Sheen	Matte 5 to 7 %
Applications	Interior: Ideal for food surfaces such as countertops, tables, and butcher blocks.
Durability	1 to 3 years
Surface Types	Wood, cork
Advantages	Refreshes without stripping Abrasion resistant Protects against water, alcohol, and stains Washable and durable
Coverage	Softwoods : 190 to 265 ft ² /L Hardwoods : 265 to 360 ft ² /L
Compatibility	Can be covered with: Secondo, Secondo Mono, Secondo Cera, Secondo Fast. Always perform a preliminary test to ensure product suitability and compatibility. Can be applied over: Oils, stains, waxes, and chalk paints. Can be covered with: Oils, varnishes, waxes, hybrid finishes, lacquers, and paints.
Composition	Blend of vegetable oils, vegetable wax, iron oxides, isoparaffin, lead-free and cobalt-free drier.
COV	299 g/L
Viscosity	55 sec. +/- 5 sec. with #4 Ford Cup (Clear)
Origin	Canada
Tools Cleaning	Prato-Verde Tools Cleaner and Thinner
Disposal of accessories and residues	After use, soak the rags in water or lay them flat to dry before disposal. Wipe off any liquid residue before recycling the container. Any leftover product should be brought to your municipality's eco-center.
Maintenance	For regular cleaning: SECONDO CLEAN To revive shine and enhance protection every 2 to 3 months: SECONDO MAINTENANCE For intensive cleaning (degreasing, deep cleaning), as needed: SECONDO PREP
Storage and Shelf Life	Keep the product in a sealed container at a temperature between 10°C and 25°C for storage. Under these conditions, the product will maintain its quality for at least 5 years. If the product has been exposed to cold temperatures, allow it to return to room temperature for 24 hours before using.
Guarantee	Guarantee: Prato-Verde guarantees the quality of its products. They conform to the description provided in the technical data sheets and on the labels suitable for the intended use, in accordance with the instructions written by the company. However, since the manufacturer has no control over the circumstances, methods, and conditions of use, this guarantee only covers the high quality of Prato-Verde products.

Technical Specifications Preparation

1. Apply at a temperature above 15 °C.
2. Ensure the wood is free from any previous finish and meticulously sanded with 100 or 120 grit sandpaper.
3. Remove dust using a vacuum cleaner.
4. After sanding, it is recommended to clean the wood with PRATO PREP to remove dust particles, reduce tannins, and enhance colour intensity.
5. Perform a product test on a hidden surface and let it dry for 24 hours to confirm the result, as it may vary depending on the type of wood used.

Technical Specifications Application

Manual Application:

1. Thoroughly mix with a stick before and during application.
2. Apply in a thin coat, using circular motions, until the wood is saturated using a STAIN APPLICATOR, POLYCOTTON RAGS, stain applicator, short-haired roller, or brush.
3. After 5 to 15 minutes, wipe the surface dry with clean POLYCOTTON RAGS to remove any excess oil.
4. Clean tools and accessories used with TOOLS CLEANER AND THINNER, and soak oil-saturated cloths in water before disposing of them in the trash.
5. Allow 18 to 24 hours to dry.
6. Repeat all previous steps for the application of the second coat.
7. For furniture application, it is recommended to sand with 000000 steel wool or 800 grit sandpaper between coats to smooth the finish.

Mechanical Application:

1. Thoroughly mix with a stick before and during application.
2. Apply the oil using a brush or short-haired roller.
3. After 5 to 15 minutes, polish using a floor polisher with a white or beige pad.
4. If there is excess oil after polishing, place a POLYCOTTON RAG under the pad and run the polisher again to remove excess oil. Replace the cloth when saturated with oil.
5. Alternatively, apply the oil directly with the polisher by adding a small amount of oil to the center of the pad and rubbing until the product is evenly applied.
6. Clean tools and accessories used with TOOLS CLEANER AND THINNER, and soak oil-saturated cloths in water before disposing of them in the trash.
7. Allow 18 to 24 hours to dry.
8. Repeat all previous steps for the application of the second coat.

Further Treatment

The greatest advantage of oil in wood treatment lies in its ease of maintenance and repair. The key to well-maintained oiled wood is prevention. The longer the interval between treatments, the longer the process will take. When SECONDO CLEAN and SECONDO MAINTENANCE products are no longer sufficient to keep your oiled wood in good condition, it's a sign that it's time to consider applying a new layer of oil.

Good general condition (Less resistance against liquids):

1. Clean the wood with SECONDO CLEAN.
2. Apply a coat of TAVOLO according to the product instructions.
3. No sanding or stripping required.

Good general condition (Stains or small damaged areas):

1. Sand the damaged area with 120-grit sandpaper.
2. Apply two coats of TAVOLO finishing oil to the sanded area following the product instructions.

Medium general condition (Slight discolouration, multiple stains, reduced resistance against liquids):

1. Clean the wood with SECONDO PREP.
2. Apply two coats of TAVOLO according to the product instructions.
3. No sanding or stripping required.

Poor general condition (Severe discolouration, graying surface, no resistance against liquids, many stains or damaged areas):

1. If cleaning with SECONDO PREP does not remove the stains and graying, restart the entire procedure with the TAVOLO product.

Tips

Colours can be mixed to create unique shades. For a less intense colour, mix with Tavolo Colourless. The colour 00 - Colourless provides an amber finish and enhances the wood grain. The colour 22 - Natural is slightly whitened and helps preserve the whiteness of light woods (pine, maple, cherry, spruce, beech, aspen, etc.). It's strongly recommended to perform a test beforehand on open-grain and coloured woods (oak, walnut, mahogany, elm, etc.). For a smoother and softer finish, lightly sand between the last two coats with a 600 or 800 grit sandpaper.

WARNINGS

Keep out of reach of children. Keep away from flames or sparks.

DANGER OF COMBUSTION: Materials such as rags used with this product may begin to burn by themselves. After use, put rags in water or lay flat to dry, then discard.